



Technical Data Sheet

DESCRIPTION

GYVLON FLOWING SCREED is a blend of **GYVLON BINDER** and selected aggregates mixed with clean potable water to produce a flowing pumpable screed (manufactured to BSEN 13813:2002) which is ideal for application over warm water and electric underfloor heating systems.

USES

GYVLON FLOWING SCREED is designed to provide a smooth level surface in both commercial and domestic buildings prior to the application of floor finishes and is particularly suitable to application as a floating screed and for use with underfloor heating systems.

FEATURES

- Increased productivity - 2000m²/day can be easily achieved. (average 500-1000 m²/day).
- Can be walked on in 24-48 hours.
- Does not require curing.
- Extremely low shrinkage - does not curl and minimises the risk of cracking.
- Suitable for floating floor construction.
- Avoids the need for reinforcement.
- Ideal for use with underfloor heating systems enabling rapid commissioning of the underfloor heating in accordance with BS1264:2001-Part 4 clause 4.4.
- Significantly reduced thickness when compared to traditional sand - cement screed.
- Weight saving as a result of thinner section.
- Large bay sizes of up to 30-40 linear meters depending on application.
- Dries at a rate of 1mm per day up to a screed depth of 40mm however this can be affected by adverse site conditions.
- Can be force dried as early as 7 days after application.
- Easily achieves SR2 finish as described in BS8204.
- Protein free - cannot harbour harmful bacteria.
- Non combustible (tested to BS476 Part 4).
- Minimal Thermal expansion (0.012mm/mK).
- Excellent thermal conductivity (2.2W/mK).
- Self compacting

TECHNICAL DATA

Appearance/Colour:	Off-white fluid mortar
Water demand:	15-18 % b.w
pH:	> 10
Wet Density:	2200 kg/m ³
Dry Density:	2000 kg/m ³

Typical Screed Properties:

Binder content (kg/m ³)	675-750
Setting Time BSEN196.3 Vicat (Hrs):	< 10 - 12
Compressive Strength:	> 25.0
Flexural Strength:	> 5.0

MINIMUM APPLICATION THICKNESS

Bonded:	25mm
In contact with substrate:	30mm
Unbonded:	30mm
Floating Commercial:	40mm
Floating Domestic:	35mm
Underfloor Heating:	30mm minimum to cover pipes.

DELIVERY

GYVLON FLOWING SCREED is supplied in bulk via a concrete plant in 5m³ mixer trucks.

HEALTH & SAFETY

Some of the components of this product may be hazardous during mixing and application.

Please consult the relevant Health & Safety Data Sheets, available from Lafarge on request and provided with each delivery.

Issue 2—Revision 0—01-12-10

Lafarge Gyvlon Limited

Unit 221 Europa Boulevard,
Westbrook, Warrington WA5 7TN

sales@gyvlon.co.uk
01925 428780



www.gyvlon.co.uk



Calcium Sulfate binder
EN 13454-CAB-30



greenspec®